

**TECHNICAL DATA****ULTRA-MATE[®] 820****Construction characteristics**Construction
Base material

Width

Overall thickness

Weight

Hooks / cm²**Usage characteristics**

Peel Strength with Loop 001*

Shear Strength with Loop 001*

Breaking Strength*

Melting point

Washing resistance

U.V. resistance

Acid resistance

Humidity resistance

Sewn resistance

Flammability (MVSS302)

Extruded
Polyamide 6.6Nominal ± 1 mm 1.52 ± 0.03 mm 490 ± 50 g/m²

Average 60

Minimum 2.4 N/cm

Minimum 18 N/cm² 165 ± 35 N/cm

250°C

Medium

Medium

Medium

Medium

Good

Maximum 100 mm/minute

* Internal norm of VESA

The information included in this Technical Sheet is based on reliable tests and trials. Average value as a reference only, not a nominal specification. Given the diversity of uses of our products we advise our customers to assure themselves that the product meets the requirements of their application. The responsibility for the application and use of the product remains with the customer.

Elaborado: J.C. Lima**Revisado:** E. Ducet**Autorizado:** J. Camarillo**Fecha:** 09.07.12**ANEXO: IDT – 605-B****FTP 621 Versión 2**