



TECHNICAL DATA

ULTRA-MATE[®] 805

Construction characteristics

Basic construction
Base material

Width

Overall thickness

Weight

Hooks/cm²

Usage characteristics

Peel Strength with Velour std*

Shear Strength with Velour std *

Melting Point

Washing resistance

U.V. rsistance

Acid resistance

Humidity resistance

Sewn resistance

Flammability (MVSS302)

* Internal norm of VESA

Extruded
Polyamide 12

Nominal ± 1 mm

1.00 ± 0.10 mm

400 ± 24 g/m²

Average 137

Minimum 0.6 N/cm

Minimum 8.0 N/cm²

169°C

Good

Medium

Medium

Medium

Good

Maximum 100 mm/minute

The information included in this Technical Sheet is based on reliable tests and trials. Average value as a reference only, not a nominal specification. Given the diversity of uses of our products we advise our customers to assure themselves that the product meets the requirements of their application. The responsibility for the application and use of the product remains with the customer.

Elaborado: J.C. Lima

Revisado: E. Ducet

Autorizado: J. Jacobs

Fecha: 17.10.11

ANEXO: IDT – 605-B

FTP 610 Versión 2